



Yeşilbayır Mah. Şimşir Sk. No: 22 Hadımköy - İstanbul/TÜRKİYE Tel: 0212 771 13 71 Fax: 0212 771 38 88

710 STONE & MARBLE KIT

STONEKIT ADHESIVE is an adhesive set consisting of high viscosity cyanoacrylate and activator, which is developed especially for **bonding** materials such as natural stone, marble, granite and decorative stones.

FEATURES & BENEFITS

- Ability to bond rapidly in seconds,
- High bonding power
- Thanks to its high viscosity formula, it can be used in vertical places without pour and splash,
- Activator makes it possible and incredibly fast to bond even porous surfaces,

APPLICATIONS

- Utilized in assembly and repairs of parts such as natural stone, marble, granite, wood, MDF and metal,
- Preferred especially in the applications which require rapid curing.

Ability to Bond Rapidly in Seconds

INSTRUCTIONS

- One of the substrates need to be smooth and have a good connection area.
- Apply a drop on one of the substrates and use spray on the other one.
- Join substrates and press firmly for approximately one minute.
- Application temperature is between +5°C and +35°C.
- Dry gel can be cleaned with Akfix DEBONDER.

RESTRICTIONS;

- Cyanoacrylates should ideally be stored in original sealed containers until used.
- Avoid exposure to strong light and heat sources
- Cyanoacrylates can bond to skin within seconds
- Do not drip into skin or into eyes can cause serious injury to your eyes.
- Will become hard in container if not closed properly!
- Activator is flammable. Do not throw into fire.
- Activator box is pressured. Do not crush or drill.





Yeşilbayır Mah. Şimşir Sk. No: 22 Hadımköy - İstanbul/TÜRKİYE Tel: 0212 771 13 71 Fax: 0212 771 38 88 🔰 www.akfix.com - info@akfix.com

STORAGE AND SHELF LIFE;

12 months between 5 and 25 °C in closed original packaging.

PROPERTIES

<u>Glue</u>

Basis	: Ethyl Cyanoacrylate	
Appearance	: Liquid gel	
Color	: Colorless	
Application Temperature	: +5°C to +35°C	
Density	$: 1.06 \pm 0.01 \text{gr/cm}^3$	ASTM D1875
Flashpoint	: >81 °C	
Viscosity	: 1200 - 1800 Cps at 25°C	ASTM D1084
Temperature Resistance	: -20°C to +70 °C	

Activator

Basis	: Hexane
Appearance	: Aerosol
Color	: Colorless
Application Temperature	: +5°C to +35°C
Temperature Resistance	: -20°C to +70 °C

PRODUCT

Product Type	Volume / Weight	Package
Activator & Glue	100 mL + 25 gr	48
Activator & Glue	250 mL + 65 gr	24
Activator & Glue	500 mL + 125 gr	24

DISCLAIMER

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in maccordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.